

USG Calcium Sulfate Feed Grade Gypsum

	Location	Chemical Analysis				Screen Analysis	
		Calcium Sulfate Dihydrate (CaSO ₄ ·2H ₂ O)		Calcium (Ca)	Sulfur (S)	Plus 100 Mesh	Minus 100 Mesh
		Typical	Minimum Guarantee				
Fine Grind	Empire, NV	84%	82%	19.6%	15.7%	4%	96%
	Fort Dodge, IA	90	86	20.9	16.7	10	90
Coarse Grind	Detroit, MI	89%	88%	20.7%	16.6%	76%	24%
	→ Shoals, IN	88	85	20.5	16.4	78	22

